

**Industrial Flooring**

**100% SOLIDS MME**

Moisture-Mitigating High-Build Epoxy for Direct-To-Concrete Application

**Description:** Eco-CorFlex 100% Solids MME is a two-component epoxy primer specifically formulated for concrete floors experiencing mild to severe moisture vapor transmission (MVT) issues. MME is capable of controlling moisture emission rates exceeding 20 lbs per square inch. This moisture vapor barrier is ideal beneath floor coatings, tile, VCT, vinyl, carpet, and wood flooring, providing essential protection for long-lasting results.

**Areas of Usage:** When used in combination with the appropriate topcoat, for use in both interior or exterior installations including garages, basements, warehouses, manufacturing facilities, parking lots, storage areas, labs, airplane hangars, washrooms, showers, patios, walkways and handicap ramps.

<b>Features / Advantages:</b>	2:1 pigmented primer	Extreme quick-cure properties
	Moisture-mitigating system	Dry time accelerated on cool substrates
	Direct-to-concrete application	Outstanding flow and leveling
	For use in full-chip applications	Superior adhesion
	Interior & exterior applications	Zero VOCs and low odor
	MVP for all types of flooring	Molecularly bonding

**Surface Preparation:** Allow new concrete to cure for at least 30 days prior to preparation and coating. Test for moisture. Remove dust, oil, grease, curing compounds, scale and other contaminants. Prepare concrete via mechanical abrasion (grinding, diamond grinding, abrasive blasting, shot blasting) to achieve a surface profile equivalent to CSP3 to CSP5. Grinding & diamond grinding procedures are outlined in SOP GFC-106, titled Concrete Preparation.

**Technical Data:** Note: Data / results may differ due to statistical variations, mixing methods and equipment, temperature, application methods, actual site conditions and curing conditions

**Packaging:** Part A and Part B Activator - 5 gallon containers (59 lbs, 56 lbs and 45 lbs for Part A Tumbleweed, Part A Silver Gray and Part B, respectively). Approximate weight (may vary depending upon pigment and fill level).

**Mixing Ratio:** Two parts colored resin (Part A) to one part catalyst (Part B), i.e., 2:1 ratio by volume. The mixture may be diluted with solvent (typically xylene denatured alcohol) using 1 deli cups/gallon (Ratio = 2:1:1/8).

**Application:** 9", 14" or 18" rollers with microfiber nap and polyester brush. **Application is recommended for horizontals only** (see "Application Procedures on page 3 for details).

**Average Dry Time at 77°F (25°C):** Dry times vary depending upon weather conditions. **Cure to Tack-Free:** Typically 2-4 hours; **Cure to Tack Form:** <2 hour; **Waiting Time Between Coats:** 2-4 hours **Full Cure:** 24 hours.

**Industrial Flooring**

**100% SOLIDS MME**

Moisture-Mitigating High-Build Epoxy for Direct-To-Concrete Application

<b>Technical Data (Cont.):</b>	<i>Data / results may differ due to statistical variations, mixing methods and equipment, temperature, application methods, actual site conditions and curing conditions</i>
Reducing:	May be reduced with e.g., xylene, acetone or denatured alcohol (before reducing, consult local air district rules or regulations). In warm temperatures use 1 deli cup solvent/gallon of %100 Solids MME.
Finish:	Not applicable
Colors:	Tumbleweed, Silver Gray, Black and Clear
% Solids (Vol):	100% solids
Pigment Type:	Chemical resistant
Tensile Strength:	8700 psi (ASTM D638)
Tensile Elongation:	6.6% (ASTM D638)
Flexural Strength:	15700 psi (ASTM D790)
Volatile Content:	0 g/l (ASTM 2369)
Thickness:	Recommended minimum for application is 12 mils dry film thickness. Two (2) gallons Part A and one (1) gallon of Part B (3 gallons total) will typically cover up to 400 sq ft at 12 mils thickness depending of porosity of substrate.
Compressive Strength:	13300 psi (ASTM D695)
Durometer Hardness (Shore D)	87.5 (ASTM D2240)
Tabor Abrasion (CS17 Wheel):	1 kg load /1000 cycles - <80 mg
Pot Life:	Extreme quick-cure properties. <i>Pot life applies to material poured immediately onto the substrate following preparation.</i> Pot Life = 45 minutes at 40°F (4°C); 30 minutes at 70°F (24°C); and 20 minutes at 92°F (33°C).
Shelf Life:	12 months at 77°F (25°C) when Parts A and B are not combined

## 100% SOLIDS MME

Moisture-Mitigating High-Build Epoxy for Direct-To-Concrete Application

**Mixing:** Pigmented 100% Solids MME is a two-component system: Part A and Part B (activator). **Pre-measure Parts A, B and solvent.** Thoroughly mix the pigmented Part A component separately, ensuring a uniform color. Then, add 2 parts Part A and 1 part Part B in a bucket. **Mix immediately. Within 20 secs, add solvent and re-mix. DO NOT EXCEED 1 MINUTE OF MIXING. IMMEDIATELY POUR THE PRODUCT OUT OF THE CONTAINER.**

**Application Procedure:** 100% Solids MME is a quick-cure epoxy for use by trained/experienced applicators only. Pigmented 100% Solids MME is **typically used in full-chip coating systems as a moisture-mitigating primer coat.** Apply using 9", 14" or 18" rollers with microfiber nap; use a polyester brush for nooks and crannies. **NOTE: Because of %100 Solids MME's quick-cure properties, this product is not to be poured into e.g, deli cups for priming stem walls; it will "cook" in the container. Instead, use Hydro Polymer Yellow Label (4:1) for priming stem walls.**

**Handling & Storage:** Store in a cool, dry, well-ventilated area. Keep containers tightly closed.

**• KEEP CONTAINER TIGHTLY CLOSED • KEEP OUT OF REACH OF CHILDREN  
• NOT FOR INTERNAL CONSUMPTION • INDUSTRIAL GRADE • HANDLING  
AND INSTALLATION MUST BE PERFORMED BY ECO-CORFLEX-CERTIFIED  
APPLICATORS ONLY •**

All information provided by Eco-CorFlex concerning its products, including but not limited to, any recommendations and advice relating to the application and use, is given in good faith based on Eco-CorFlex's current experience and knowledge of its products when properly stored, handled and applied under normal conditions in accordance with Eco-CorFlex SOPs. In practice, the differences in materials, substrates, storage and handling conditions, actual site conditions and other factors outside of Eco-CorFlex's control are such that Eco-CorFlex assumes no liability for the provision of such information, advice, recommendations or instructions related to its products, nor shall any legal relationship be created by or arise from the provision of such information, advice, recommendations or instructions related to its products. The user of Eco-CorFlex product(s) must test the product(s) for suitability for the intended application and purpose before proceeding with the full application. Eco-CorFlex reserves the right to change the properties of its products without notice.

Prior to each use of any Eco-CorFlex product, the user must read and follow the warnings and instructions on the products most current Technical Data Sheet, product label and Material Safety Data Sheet which are available online at [www.ecocorflex.com](http://www.ecocorflex.com) or by calling Eco-CorFlex at 866-406-2628. Eco-CorFlex warrants this product to be free of manufacturing defects and warrants this product to meet the technical properties on the current Technical Data Sheet if used as directed within the shelf life. The user must determine suitability of each product for its intended use and assumes all risks. The buyer's sole remedy shall be limited to the purchase price or replacement of the product *exclusive of labor or cost of labor.*

**ECO-CORFLEX MAKES NO OTHER WARRANTY, EXPRESSED OR IMPLIED, AND ALL WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE ARE HEREBY DISCLAIMED**